



**ANYMATS RT - MODULAR RUBBER** 



TECHNICAL INFORMATION		
20 MM	40x40 CM	17.50 KG/M2
25 MM	40x40 CM	22.00 KG/M2
30 MM	40x40 CM	26.50 KG/M2
40 MM	40x40 CM	34.00 KG/M2
25 MM	50x50 CM	22.00 KG/M2
30 MM	50x50 CM	26.50 KG/M2
40 MM	50x50 CM	34.00 KG/M2

TECHNICAL VALUES		
Critical Height of Drop	0,94 M (HIC Coefficient- TSE General Security Rules)	
Flammability	76 / 769 / EEC Compliance with Directives	
Abrasion	0,036 μm	
Endurance	19,18 Mpa / cm²	
Water Permeability	%1,85	
Density	0,910 gr/cm <sup>3</sup>	
Resistance to Cigarette	TS 11900 EN 1399 Compliance with Norms	

APPLICATION METHOD		
PU Glue	Double component glue is mixed. Approximately 1.00 KG / m2 is applied with a treaded trowel between 30 and 40 minutes.	
Modular Rubber	The modular rubbers are lined up side by side at desired pattern so that there is no gap, and they are placed with hammer.	

COLORS		
Glue	Red, Green	
Modular Rubber	Red, Green, Black	



PRODUCT PACKAGING		
Glue 10 KG (9+1) or 24 KG (21+3) Plastic/Metal Buckets.		
Modular Rubber	It is properly stacked on the pallets. Protected by plastic packaging.	

PRODUCT STORAGE		
Glue Unopened packages can be stored between +5 and +30 degrees for 12 months.		
Modular Rubber	Unopened packages can be stored between +5 and +30 degrees for 12 months.	

PRODUCTION AND INSTALLATION PERIODS			
Glue	Production: 1-5 Days	Installation: 1-5 Days	Can not work simultaneously
Modular Rubber	Production: 3-10 Days	Installation: 1-5 Days	Can not work simultaneously

WARRANTY PERIODS		
UV	5 YEARS	% 5 Tolerance
Abrasion	3 YEARS	%10 Tolerance
Installation Warranty	1 YEAR	5 years with maintenance contract

## **ANYMATS RT - MODULAR RUBBER**

## **EXAMPLES OF APPLICATIONS**













Merkez/Head Office: Metro 34 Plaza No: 23/100, İOSB Bedrettin Dalan Bulvarı Başakşehir - İstanbul / TÜRKİYE

Fabrika/Factory: Velimeşe OSB 93. Sokak No:101 Çorlu - Tekirdağ / TÜRKİYE